

3M

Scotch-Weld™

Industrial Adhesive

4475

Technical Data

December, 2010

Features

- Dries quickly to a firm bond.
- Excellent resistance to water, plasticizer migration, many detergent and soap solutions, oils and grease.
- A general purpose adhesive for bonding most vinyls, ceramics, glass, leather and cloth to a variety of substrates.

Typical Physical Properties

Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Viscosity	6,500 - 10,500
Brookfield Viscometer	RVF #5 sp. @ 20 rpm @ 80°F
Solids Content (approx.)	41-45% (by wt.)
Base	Synthetic Resin
Color	Clear
Net Weight	8.3 lbs./gal.
Flash Point	20°F CC
Coverage	487 sq. ft. per gallon (1 Mil Dry Film)
Solvent	methyl ethyl ketone (MEK)

3M™ Scotch-Weld™ Industrial Adhesive 4475

Application Equipment Suggestions

Note: Appropriate application equipment can enhance adhesive performance. The user is responsible for evaluating application equipment in light of the user's particular purpose and method of application.

1. Pumping

5-Gallon Pail Dispensing System

Pump – 9:1 ratio double acting ball check type pump, 11.0 cubic inches per cycle, 4¹/₄" diameter air motor minimum.

Pail cover to be used to reduce solvent loss.

55-Gallon Drum Dispensing System

Pump – 10:1 ratio double acting ball check type pump, 11.0 cubic inches per cycle, 4¹/₄" diameter air motor minimum, Bung mount type.

2. Accessories

Hose – 1000 psi minimum working pressure, nylon lined. Flow rate at 40°F, 20 ft. of ³/₄-ID plus 10 ft. ¹/₂-ID and a flow gun equals 1 pound/minute at pump air pressure of 75 psi.

3. Chemical Resistance Requirements

Synthetic materials in contact with this product must be resistant to ketones and aromatic solvents. Compare, nylon or PTFE coatings are suggested for packings and gaskets.

Handling/Application Information

Directions for Use

- 1. Surface Preparation:** Best results are achieved on clean, dry surfaces. Oil, grease and other contaminants can be removed by wiping with a solvent such as methyl ethyl ketone (MEK).*
- 2. Application:** Apply adhesive to one or both surfaces (best results are obtained by coating both surfaces) and bond immediately using firm pressure.
- 3. Drying Time:** Allow to dry a minimum of 24 hours for maximum strength.
- 4. Cleanup:** Remove unhardened or hardened material with cloth dampened with a solvent such as methyl ethyl ketone (MEK).*

***Note:** When using solvents, extinguish all ignition sources and follow the manufacturer's precautions and directions for use.

3M™ Scotch-Weld™ Industrial Adhesive 4475

Typical Physical Properties

Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

180° Peel Strength – Canvas/Steel		
Time @ 75°F	Test Temp.	Value (lbs./in. width)
1 day	75°F	13
3 days	75°F	24
5 days	75°F	27.5
7 days	75°F	32.5
2 wk.	75°F	35
3 wk.	75°F	44
after 3 wk.	-30°F	22
after 3 wk.	150°F	17
after 3 wk.	180°F	7

Storage

Best storage temperature is 60-80°F (16-27°C). Higher temperatures reduce normal storage life. Lower temperatures cause increased viscosity of a temporary nature. Rotate stock on a “first in, first out” basis.

Shelf Life

When stored at the recommended temperature in the original, unopened container, this product has a shelf life of 15 months.

3M™ Scotch-Weld™ Industrial Adhesive 4475

Precautionary Information

Refer to Product Label and Material Safety Data Sheet for health and safety information before using this product. For additional health and safety information, call 1-800-364-3577 or (651) 737-6501.

Technical Information

The technical information, recommendations and other statements contained in this document are based upon tests or experience that 3M believes are reliable, but the accuracy or completeness of such information is not guaranteed.

Product Use

Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. Given the variety of factors that can affect the use and performance of a 3M product, user is solely responsible for evaluating the 3M product and determining whether it is fit for a particular purpose and suitable for user's method of application.

Warranty, Limited Remedy, and Disclaimer

Unless an additional warranty is specifically stated on the applicable 3M product packaging or product literature, 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY OR CONDITION ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. If the 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

Limitation of Liability

Except where prohibited by law, 3M will not be liable for any loss or damage arising from the 3M product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.

ISO 9001:2008

This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9001:2008 standards.



Industrial Adhesives and Tapes Division

3M Center, Building 225-3S-06
St. Paul, MN 55144-1000
800-362-3550 • 877-369-2923 (Fax)
www.3M.com/industrial



Recycled Paper
40% pre-consumer
10% post-consumer

3M and Scotch-Weld are trademarks of 3M Company.
Printed in U.S.A.
©3M 2010 78690002478 (12/10)